	ALLOYS & BLENDS											
GPL	SYNOFIN(PC/PO)											
Properties	STANDAR D ASTM	Unit	HA4701 M500 (PC/PO)									
Flow												
Melt Flow Index @ 260C & 2.16 Kg load	D1238	gms/10 min	12 - 30 (300C&1.2 Kg)									
Mechanical												
Tensile Strength @ Yield 50 mm/min	D638	MPa	50 - 60									
Tensile Elongation @ Yield	D638	%	10 -14									
Flexural Strength 5 mm/min	D790	MPa	65 - 88									
Flexural Modulus	D790	MPa	1800 - 2800									
Izod Notched Impact Strength	D256	J/m	800 - 1000									
Thermal												
Heat Deflection Temperature Under Load (B)1.82MPa	D 648	С	125 - 132									
Vicat Softening Temperature (B)	D 1525	С	148- 154									
Others												
Density	D 792	gms/cc	1.14 - 1.18									
Flammability Test @ 3mm thickness	UL 94											
Filler Content	D 5630	%	-									
Hardness	D 2240	Shore D	-									

^{*} Typical values represent an average for the samples tested using standard procedures.

The data indicated are intended as guides and do not reflect product specifications for any particular property

All information, direction or advice given by Gujarat Petrosynthese Ltd (GPL) as to the performance, characteristic, application, design or use of these material is given in good faith and the best of its knowledge. However, as GPL has no control over the use to which others put these materials, it does not accept any responsibility or any liability therefrom in connection with any services rendered by it or for the design, characteristic, performance of the materials either towards any purchaser or user thereof or towards any third party. Each user of these materials should make his own tests to determine the material's suitability for his own particular use. GPL or any of their subsidiary companies or distributors can not be held responsible for any loses incurred by incorrect use of material. In accordance with the policy of these companies of continuous product development, users are advised to check the most up to date information.

GUJARAT PETROSYNTHE	SE LIMITED
Polymer Alloys & Blends Division	Agents:
No.24, II Main, Phase I, Doddanekkundi Indl. Area	
Mahadevapura Post, Behind Graphite India Ltd., Bangalore-560048	
Phone: 91-080-28524133 Fax: 91-080-28524171. E-mail: inf@gpl.in	
No.24, II Main, Phase I, Doddanekkundi Indl. Area Mahadevapura Post, Behind Graphite India Ltd., Bangalore-560048	Agents: